

ForestrySA MLR Export Product Specifications

| Product | Diameter Sedub –Ledub (Av) | Small End Marking | Length (m) | Knots | Spike Knot | Sweep | Wobble | Nodal Swelling | Butt Tears (mm) | Surface Defects |
|------------|----------------------------|-------------------|--------------|----------------------------------|----------------------------------|-----------------------------|--------|--------------------------------------|-----------------|--------------------------|
| AAX | 420-Open (Nil) | 100% | 3.88 5.88 | Sed/3 <120 <3/m > 50mm | 1 60mm/4m | Sed/4 | Sed/6 | Sed < 300 < 50mm Sed > 300 < 70mm | < 50 | < 30mm |
| ASW | 320 – Open (360) | 100% | 3.88 5.88 | Sed/3 <120 <3/m > 50mm | 1 60mm/4m | Sed/4 | Sed/6 | Sed < 300 < 50mm Sed > 300 < 70mm | < 50 | < 30mm |
| KDS | 220 – 360 (280) | 100% | 3.88 5.88 | Sed/3 <120 <3/m > 50mm | 1 60mm/4m | Sed/4 | Sed/6 | Sed < 300 < 50mm Sed > 300 < 70mm | < 50 | < 30mm |
| SPS | 170 – 260 (Nil) | 100% | 3.88 5.88 | Sed/3 <120 | No | Sed/2 | Sed/6 | < 50mm | < 80 | < 30mm |
| KIG | 320-Open (Nil) | 100% | 3.88 | Sed/2 <240 <3/m > 100mm | 1 100mm/4m | Sed/2 | Sed/2 | Ok | < 50 | 1/2.4m inc 240mm knot |
| P10 | 110-240 (Nil) | NA | 3.88 5.88 | Must be cut flush with main stem | Must be cut flush with main stem | >200 Sed/1.5 < 200 Sed/1 | Sed/1 | Ok if debarking possible | Nil | Ok if debarking possible |
| P12 | 130 – 240 (Nil) | NA | 3.88 5.88 | Must be cut flush with main stem | Must be cut flush with main stem | >200 Sed/1.5 < 200 Sed/1 | Sed/1 | Ok if debarking possible | Nil | Ok if debarking possible |

Length tolerance. At least the length designated at the shortest point & may exceed the designated length by up to 100 mm.

Docking. Logs shall be cleanly docked and square. Side tears & Sloven ends are not acceptable.

Scar face. Not acceptable for pulp, slits removed for KMS & KIG, ≤ 50mm for A & K.

Trimming. Branches shall be trimmed flush to main stem.

Dryside / Decay / Insect – Not Permitted.

Shape. Abrupt diameter changes by more than 20% are not permitted.

Moisture. Delivered within 14 days.

Blue Stain. Accepted only with prior approval. External blue fungi appearance acceptable

Cleanliness. Not to contain charcoal, stones, mud / dirt, wire or metal.

Log Roundness. Longest face ≤1.25 times the shortest face for A, K, KIG & ≤ 1.3 times for KMS.